


PRODUCT INFORMATION SHEET

CE-1214, Methyl Laurate/Myristate (Methyl Dodecanoate/Tetradecanoate)

DESCRIPTION



Is predominately comprised of Methyl Laurate (C12, 65-75%) and Methyl Myristate (C14, 21-28%); 'R' in the structural diagram above represents a saturated alkyl chain of carbon atoms equal to 11 or 13. Not including the methyl ester group, there are an even number of carbon atoms in the molecule. It is a clear to yellow liquid under ambient conditions with a musty odor.

CAS/EC Number: 308065-15-8 / 629-776-4

PRODUCT NOTES

PHYSICAL PROPERTIES:

(All properties @ 760mmHg unless stated)

Specific Gravity: 0.9
 Vapor Pressure: <0.55 Pa at 25°C
 Melting Point: 6.5°C
 Viscosity: 3.65 mPa.s t 20°C
 Boiling Point: 261.85 - 295.85°C

Insoluble in water under ambient conditions, but suitable solvents include ethyl ether, and mineral oil. May attack, swell and soften rubber and plastic. Concrete swells and deteriorates with contact. Glycerine can settle out in storage.

GENERAL INFORMATION

APPLICATION USES

Potential intermediate and end use applications include soapmaking, agriculture, amides, chlorinated lubricants, cutting oils, defoamers, gear oils, isopropyl esters, jet lubricants, methyl ester sulfonates, plasticizers, PEG Esters, rolling oils, sulfurized lubricants, metalworking fluids, production of plasticizer alcohols, emulsifiers, stabilizers, resins, flavorings, fracking fluids, and solvents for inks, paint removal, and other applications.

OIL DERIVATION/ALLERGEN/BSE/MICROBIAL

- All of our brands are produced in P&G Chemicals' global network. They are manufactured from naturally occurring vegetable oils.
- Bovine Spongiform Encephalopathy (BSE) and Transmissible Spongiform Encephalopathy (TSE) are not a concern.
- No gluten/wheat, corn, dairy, egg, fish/shellfish, sulfites, yeast, starch, MSG, peanut, other nut, rice, potential allergens are present. No preservatives or additives are present
- At the low vacuum and high temperature at which our process operates, our products are not micro-susceptible.

RETEST DATE

Stability is affected by how a product is stored. We expect the product to be stable if it is kept under the recommended Storage and Handling conditions. We recommend retesting the product for Sensitive Properties every 24 months. (Information listed in Storage and Handling section)

P&G CHEMICALS DOES NOT PROVIDE SHELF LIVES OR EXPIRY DATES.

STORAGE AND HANDLING (recommended)

Storage Temp Targets: Target: 20 °C (68°F)
 Max Steam, psi: 150
 Load out filter (reco): 5 micron
 Sensitive Properties: Color, Moisture, Acid Value
 Railcar or Tank Truck: Carbon Steel
 Storage Tank: Carbon Steel

Handling Temp Min-Max: Max: 32°C (90°F)
 Agitation/Recirculation: Yes, if heating medium > 100°C
 Nitrogen Blanket: Not necessary
 (<1% O₂)

Pumps and Lines: Carbon Steel

For further details, or samples of this material or other P&G Chemicals products, visit our website:

www.pgchemicals.com

IMPORTANT NOTE: This technical product information and suggestions for use, while believed to be accurate and reliable, is given without creating any guarantee or warranty of any kind expressed or implied. Purchaser assumes all risk in acting on this information provided by Procter & Gamble representatives. Since product's specifications may vary on customers' basis, each purchaser is urged to perform their own tests, experiments and investigations in the use of Procter and Gamble products and for purposes of determining compliance with applicable Federal, State and local laws and regulations. Nothing contained herein shall be construed as a recommendation to use any product in connection with existing patents covering any material or its use. Moreover, no license is to be implied under any Procter & Gamble patents relating to uses of the above.